

Metric

Typical Product Codes Supplied	P200FW to P30FW		
Nominal Thickness	0.20mm to 0.30mm		
Binder	Modified Acrylic		
	P200FW	Made to order Minimum	Made to order Maximum
Glass Type	C-glass	-	-
Fibre Diameter	12-13 μ	-	-
Weight	21-25 g/m ²	-	-
Nominal Thickness	0.2 mm	0.2 mm	1.1 mm
Binder Type	Modified Acrylic	-	-
Binder Content	13-15%	-	-
Styrene Monomer Solubility	Insoluble	-	-
Theoretical Resin Absorption	180 g/m ²	-	-
Tensile Strength	35 N/50 mm	-	-
Roll Width	-	45 mm	2.0 m
Roll Length	-	50 m	350 m

Imperial

Typical Product Codes Supplied	P200FW to P30FW		
Nominal Thickness	0.008 in. to 0.012 in.		
Binder	Modified Acrylic		
	P200FW	Made to order Minimum	Made to order Maximum
Glass Type	C-glass	-	-
Fibre Diameter	0.0005 in.	-	-
Weight	0.075 oz/ft. ²	-	-
Nominal Thickness	0.008 in.	0.008 in.	0.043 in.
Binder Type	Modified Acrylic	-	-
Binder Content	13-15%	-	-
Styrene Monomer Solubility	Insoluble	-	-
Theoretical Resin Absorption	0.590 oz/ft. ²	-	-
Tensile Strength	3.9 lbs/in.	-	-
Roll Width	-	1.77 in.	78 in.
Roll Length	-	160 ft.	1150 ft.